

DECLARATION OF PERFORMANCE	
Reference :	DOPHydroflamTGv2
Commercial name :	Hydroflam
Product type :	Fire retardant Tongue and groove panel
Reference standard :	Wood Based Panel - EN 13986+A1:2015 Annex A Table A.4
CE Class :	P5
Field of application :	Internal use as a structural component in humid conditions
AVCP Class :	1
Certification number:	1161-CPR-1323 [10 mm ≤ d ≤ 22mm (B-s2,d0); (**) 18 mm ≤ d ≤ 22mm (Bfl-s1)]
Produced at:	Ingelmunstersteenweg 299,B-8780 Oostrozebeke

Essential Characteristic	Unit	Reference	Thickness range (mm)		
			>6-13	>13-20	>20-25
Bending strength	N/mm <sup>2</sup>	EN 622-5	18	16	14
Modulus of elasticity in bending	N/mm <sup>2</sup>	EN 622-5	2550	2400	2150
Internal bond	N/mm <sup>2</sup>	EN 622-5	0,45	0,45	0,40
Swelling in thickness, 24h	%	EN 622-5	13	10	10
Moisture resistance OPTION 1 : Internal bond	N/mm <sup>2</sup>	EN 622-5	0,25	0,22	0,2
Moisture resistance OPTION 1 : Swelling in thickness	%	EN 622-5	12	12	11
Surface Soundness	N/mm <sup>2</sup>	EN 622-5	NPD	NPD	NPD
Formaldehyde class	Class	EN 13986-table B1	E1	E1	E1
Reaction to fire	Class	EN 13986-5.8	E	B-s2d0	B-s2d0 (*)
Reaction to fire (Flooring)	Class	EN 13986-5.8	NPD	Bfl-s1 (**)	Bfl-s1 (**)
Water vapour permeability μ	wet	EN 13986 - table 9	16	16	15
	dry		50	50	50
Airborne sound insulation	dB	EN 13986-5.10	NPD	NPD	NPD
Sound absorption α		EN 13986 - table 10	0,10/0,25	0,10/0,25	0,10/0,25
Thermal conductivity λ	W/m.K	EN 13986 - table 11	0,14	0,14	0,13
Strength - tension ft	N/mm <sup>2</sup>	EN 12369-1	9,4	8,3	7,4
Strength - compression fc	N/mm <sup>2</sup>	EN 12369-1	12,7	11,8	10,3
Strength - bending f <sub>m</sub>	N/mm <sup>2</sup>	EN 12369-1	15	13,3	11,7
Strength - panel shear f <sub>y</sub>	N/mm <sup>2</sup>	EN 12369-1	7	6,5	5,9
Strength - planar shear f <sub>r</sub>	N/mm <sup>2</sup>	EN 12369-1	1,9	1,7	1,5
Stiffness - tension E <sub>t</sub>	N/mm <sup>2</sup>	EN 12369-1	2000	1900	1800
Stiffness - compression E <sub>c</sub>	N/mm <sup>2</sup>	EN 12369-1	2000	1900	1800
Stiffness - bending E <sub>m</sub>	N/mm <sup>2</sup>	EN 12369-1	3500	3300	3000
Stiffness - panel shear G <sub>v</sub>	N/mm <sup>2</sup>	EN 12369-1	960	930	860
Impact resistance	Class	EN 12871	NPD	NPD	NPD
Punishing shear strength R <sub>mean</sub>	N/mm <sup>2</sup>	EN 1195	NPD	NPD	NPD
Punishing shear strength F <sub>ser,k</sub>	N/mm <sup>2</sup>	EN 1195	NPD	NPD	NPD
Punishing shear strength F <sub>max,k</sub>	N/mm <sup>2</sup>	EN 1195	NPD	NPD	NPD
Linear expansion δl <sub>30,85</sub>	mm/m	EN 318	< 3	< 3	< 3
Mechanical durability (kmod; kdef)		Shall be taken from :	NPD	NPD	NPD
Biological durability	Service Class	EN 335	1 & 2	1 & 2	1 & 2
Content of PCP	ppm	EN 13986-5.18	<5	<5	<5

(\*) <9mm : E; 9mm : D-s2,d0; > 22mm : D-s2,d0

Informative Characteristic	Unit	Reference	Thickness range (mm)		
			>6-13	>13-20	>20-25
Formaldehyde content	mg/100g	EN 120	< 8 mg/100g DS		
Reaction to fire	Klasse	BS 476	Class 1 [10 -> 25mm]		

Version date :  
6/05/2019

Lode De Boe,  
President UNILIN bvba, division panels