

DECLARATION OF PERFORMANCE	
Reference :	DOPFibrabelFRUncolouredv2
Commercial name :	Fibrabel FR Uncoloured
Product type :	MDF Fibreboard
Reference standard :	Wood Based Panel - EN13986:2004+A1:2015 Annex A Table A.9
CE Class :	L-MDF FR
Field of application :	Internal use as non-structural component in dry conditions
AVCP Class :	1
Certification number:	1161-CPR-1223 [10-15mm] ; 1161-CPR-0189 [15-30mm]
Produced at:	Rue de la Forêt 2, B-6690 Vielsalm

Essential Characteristic	Unit	Reference	Thickness range (mm)					
			6	>6 - 9	> 9 - 12	>12-19	>19-30	>30-45
Bending strength	N/mm <sup>2</sup>	EN 622-5	NPD	NPD	20	18	15	NPD
Modulus of elasticity in bending	N/mm <sup>2</sup>	EN 622-5	NPD	NPD	1700	1600	1500	NPD
Internal bond	N/mm <sup>2</sup>	EN 622-5	NPD	NPD	0.45	0.45	0.45	NPD
Swelling in thickness, 24h	%	EN 622-5	NPD	NPD	16	14	12	NPD
Moisture resistance OPTION 1 : Internal bond	N/mm <sup>2</sup>	EN 622-5	NPD	NPD	NPD	NPD	NPD	NPD
Moisture resistance OPTION 1 : Swelling in thickness	%	EN 622-5	NPD	NPD	NPD	NPD	NPD	NPD
Surface Soundness	N/mm <sup>2</sup>	EN 622-5	NPD	NPD	NPD	NPD	NPD	NPD
Formaldehyde class	Class	EN 13986-table B1	NPD	NPD	E1	E1	E1	NPD
Reaction to fire	Class	EN 13501-1	NPD	NPD	B-s2d0	B-s2d0/B-s1d0	B-s1d0	NPD
Water vapour permeability $\mu$	wet dry	EN 13986 - table 9	NPD	NPD	20	20	20	NPD
Airborne sound insulation	dB	EN 13986-5.10	NPD	NPD	12	12	12	NPD
Sound absorption $\alpha$		EN 13986 - table 10	NPD	NPD	0,10/0,20	0,10/0,20	0,10/0,20	NPD
Thermal conductivity $\lambda$	W/m.K	EN 13986 - table 11	NPD	NPD	0.1	0.1	0.1	NPD
Strength - tension ft	N/mm <sup>2</sup>	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Strength - compression fc	N/mm <sup>2</sup>	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Strength - bending $f_m$	N/mm <sup>2</sup>	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Strength - panel shear $f_v$	N/mm <sup>2</sup>	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Strength - planar shear $f_r$	N/mm <sup>2</sup>	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stiffness - tension $E_t$	N/mm <sup>2</sup>	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stiffness - compression $E_c$	N/mm <sup>2</sup>	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stiffness - bending $E_m$	N/mm <sup>2</sup>	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stiffness - panel shear $G_v$	N/mm <sup>2</sup>	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Impact resistance	Class	EN 12871	NPD	NPD	NPD	NPD	NPD	NPD
Punishing shear strength $R_{mean}$	N/mm <sup>2</sup>	EN 1195	NPD	NPD	NPD	NPD	NPD	NPD
Punishing shear strength $F_{ser,k}$	N/mm <sup>2</sup>	EN 1195	NPD	NPD	NPD	NPD	NPD	NPD
Punishing shear strength $F_{max,k}$	N/mm <sup>2</sup>	EN 1195	NPD	NPD	NPD	NPD	NPD	NPD
Linear expansion $\delta_{30,85}$	mm/m	EN 318	NPD	NPD	NPD	NPD	NPD	NPD
Mechanical durability (kmod; kdef)		Shall be taken from :	NPD	NPD	NPD	NPD	NPD	NPD
Biological durability	Service Class	EN 335	NPD	NPD	1	1	1	NPD
Content of PCP	ppm	EN 13986-5.18	NPD	NPD	<5	<5	<5	NPD

Informative Characteristic	Unit	Reference	Thickness range (mm)					
			6	>6 - 9	> 9 - 12	>12-19	>19-30	>30-45
Formaldehyde class	Class	ASTM E1333	CARB 2 < 0.11 ppm [6 -> 30mm]					
Formaldehyde class	Class	ASTM E1333	TSCA Title VI (EPA) < 0.11 ppm [6 -> 30mm]					
Reaction to fire	Class	ASTM E84	Class 1/A [6 -> 30mm]					
Reaction to fire	Class	CAN/ULC-S102	Flame Spread Rating & Smoke Developed Classification Compliant					

Version date :  
29/07/2020

Lode De Boe,  
President UNILIN bvba, division panels

