

DECLARATION OF PERFORMANCE	
Reference :	DOPFibriluxFRWheelmarkv2
Commercial name :	Fibrilux FR Wheelmark
Product type :	MDF Fibreboard
Reference standard :	Wood Based Panel - EN13986:2004+A1:2015 Annex A Table A.9
CE Class :	MDF.LA FR
Field of application :	Internal use as structural component in dry conditions
AVCP Class :	1
Certification number:	1161-CPR-1221 [6-12mm] ; 1161-CPR-0190 [12-30mm]
Produced at:	Rue de la Forêt 2, B-6690 Vielsalm

Essential Characteristic	Unit	Reference	Thickness range (mm)					
			6	>6 - 9	> 9 - 12	>=12-19	>19-30	>30-45
Bending strength	N/mm <sup>2</sup>	EN 622-5	29	29	27	25	23	NPD
Modulus of elasticity in bending	N/mm <sup>2</sup>	EN 622-5	3000	3000	2800	2500	2300	NPD
Internal bond	N/mm <sup>2</sup>	EN 622-5	0.70	0.70	0.65	0.60	0.60	NPD
Swelling in thickness, 24h	%	EN 622-5	30	17	15	12	10	NPD
Moisture resistance OPTION 1 : Internal bond	N/mm <sup>2</sup>	EN 622-5	NPD	NPD	NPD	NPD	NPD	NPD
Moisture resistance OPTION 1 : Swelling in thickness	%	EN 622-5	NPD	NPD	NPD	NPD	NPD	NPD
Surface Soundness	N/mm <sup>2</sup>	EN 622-5	NPD	NPD	NPD	NPD	NPD	NPD
Formaldehyde class	Class	EN 13986-table B1	E1	E1	E1	E1	E1	NPD
Reaction to fire	Class	EN 13501-1	B-s2d0	B-s2d0	B-s2d0	B-s1d0	B-s1d0	NPD
Water vapour permeability $\mu$	wet dry	EN 13986 - table 9	20 12	20 12	20 12	20 12	20 12	NPD NPD
Airborne sound insulation	dB	EN 13986-5.10	NPD	NPD	NPD	NPD	NPD	NPD
Sound absorption $\alpha$		EN 13986 - table 10	0,10/0,20	0,10/0,20	0,10/0,20	0,10/0,20	0,10/0,20	NPD
Thermal conductivity $\lambda$	W/m.K	EN 13986 - table 11	0.1	0.1	0.1	0.1	0.1	NPD
Strength - tension $f_t$	N/mm <sup>2</sup>	EN 12369-1	13	13	13	12.5	12	NPD
Strength - compression $f_c$	N/mm <sup>2</sup>	EN 12369-1	13	13	13	12.5	12	NPD
Strength - bending $f_m$	N/mm <sup>2</sup>	EN 12369-1	21	21	21	21	21	NPD
Strength - panel shear $f_v$	N/mm <sup>2</sup>	EN 12369-1	6.5	6.5	6.5	6.5	6.5	NPD
Strength - planar shear $f_r$	N/mm <sup>2</sup>	EN 12369-1	NPD	NPD	NPD	NPD	NPD	NPD
Stiffness - tension $E_t$	N/mm <sup>2</sup>	EN 12369-1	2900	2900	2900	2700	2000	NPD
Stiffness - compression $E_c$	N/mm <sup>2</sup>	EN 12369-1	2900	2900	2900	2700	2000	NPD
Stiffness - bending $E_m$	N/mm <sup>2</sup>	EN 12369-1	3700	3700	3700	3000	2900	NPD
Stiffness - panel shear $G_v$	N/mm <sup>2</sup>	EN 12369-1	800	800	800	800	800	NPD
Impact resistance	Class	EN 12871	NPD	NPD	NPD	NPD	NPD	NPD
Punishing shear strength $R_{mean}$	N/mm <sup>2</sup>	EN 1195	NPD	NPD	NPD	NPD	NPD	NPD
Punishing shear strength $F_{ser,k}$	N/mm <sup>2</sup>	EN 1195	NPD	NPD	NPD	NPD	NPD	NPD
Punishing shear strength $F_{max,k}$	N/mm <sup>2</sup>	EN 1195	NPD	NPD	NPD	NPD	NPD	NPD
Linear expansion $\delta_{30,85}$	mm/m	EN 318	NPD	NPD	NPD	NPD	NPD	NPD
Mechanical durability (kmod; kdef)		Shall be taken from :	NPD	NPD	NPD	NPD	NPD	NPD
Biological durability	Service Class	EN 335	1	1	1	1	1	NPD
Content of PCP	ppm	EN 13986-5.18	<5	<5	<5	<5	<5	NPD

Informative Characteristic	Unit	Reference	Thickness range (mm)					
			6	>6 - 9	> 9 - 12	>=12-19	>19-30	>30-45
Formaldehyde class	Class	ASTM E1333	CARB 2 < 0.11 ppm [6 -> 30mm]					
Formaldehyde class	Class	ASTM E1333	TSCA Title VI (EPA) < 0.11 ppm [6 -> 30mm]					
Reaction to fire	Class	ASTM E84	Class 1/A [6 -> 30mm]					
Reaction to fire	Class	CAN/ULC-S102	Flame Spread Rating & Smoke Developed Classification Compliant					
Reaction to fire	Class	IMO 2010 FTP	MED (Wheelmark) [12 -> 30mm]					

Version date :  
29/07/2020

Lode De Boe,  
President UNILIN bvba, division panels

